PRAAN naturals®

FROM NATURE WITH LOVE®

Coral Kaolin Clay
INCI: Kaolin (and) Red Iron Oxide
Product ID: CLAYKAOLINCORFR263

Specifications

Analytical Details	Methods	Specifications
Appearance:	Visual	Orange Powder
Odor:	Organoleptic	Characteristic
pH:	Not Specified	Neutral
Cationic Exchange Rate:	Not Specified	+/- 72 meq/100g
Particle Size:	Not Specified	75 µ
Composition		
Silicon Dioxide (SiO_2):	Not Specified	~66.00%
Aluminum Oxide (Al_2O_3):	Not Specified	~23.50%
Iron Oxide (Fe_2O_3):	Not Specified	~0.80%
Calcium Oxide (CaO) + Magnesium Oxide (MgO):	Not Specified	~0.50%
Potassium Oxide (K_2O) + Sodium Oxide (Na_2O):	Not Specified	~0.50%
Heavy Metals		
Arsenic (As):	Not Specified	< 3 ppm
Cadmium (Cd):	Not Specified	< 3 ppm
Mercury (Hg):	Not Specified	< 1 ppm
Lead (Pb)	Not Specified	< 10 ppm
Microbiological		
Aerobic Plate Count:	AOAC 2015.13	< 1000 cfu/g
E. coli:	AOAC OMA 2018.13	< 10 cfu/g
Total Coliforms:	AOAC OMA 2018.13	< 10 cfu/g
Salmonella:	AOAC RI 030301	Negative/25g
S. aureus	AOAC 2003.07	< 10 cfu/g
Yeast:	FDA/BAM Chapt. 18	< 10 cfu/g
Mold:	FDA/BAM Chapt. 18	< 10 cfu/g

Shelf Life: Stable (8 Years+)

Note: Traces of heavy metals are naturally present in all earths.

Date: 09/11/2024

NATURAL SOURCING

Disclaimer: All information, appearing herein on our products is based upon data that are believed to be reliable. However, it is the user's responsibility to determine the suitability of the product before use. Since the actual use of the product is beyond our control, no guarantee, express or implied, is made by Natural Sourcing of the product nor does Natural Sourcing assume any liability arising out of use, by others, of the product referred to herein.

NATURAL SOURCING®
Natural Sourcing, LLC • 341 Christian Street, Oxford, CT 06478
Phone: (203) 702-2500 • Toll Free: (800) 340-0080 • Fax: (203) 702-2501 • info@naturalsourcing.com
www.naturalsourcing.com